

GLAZED PORCELAIN TILE

Standard: EN 14411:2016 - Annex G

Product Group: Bla - GL

REFERENCE	SIZE (cm) [N]	WORK SIZE (mm)	THICK. (mm)
Freestone Grey	30x60	605x305	7.8

TECHNICAL CHARACTERISTICS	STANDARD TEST	REQUIREMENT EN14411	Value
DIMENSIONS - DEVIATION FROM THE WORK SIZE (%) - DEVIATION FROM SAMPLE AVERAGE (%)	ISO 10545-2	≤2% (Max.: ±5mm) M: 2≤ J ≤5mm ±0.9mm [7≤N<15] ±0.6% (≤±2mm)[N≥15]	COMPLIES
THICKNESS - DEVIATION FROM THE WORK SIZE (%)	ISO 10545-2	±0.5mm [7≤N<15] ±0.5% [N≥15]	COMPLIES
STRAIGHTNESS - DEVIATION FROM THE WORK SIZE (%)	ISO 10545-2	±0.75mm [7≤N<15] ±0.5% (≤±1.5mm) [N≥15]	COMPLIES
SQUARENESS - DEVIATION FROM THE WORK SIZE (%)	ISO 10545-2	±0.75mm [7≤N<15] ±0.5% (≤±2mm) [N≥15]	COMPLIES
FLATNESS - DEVIATION FROM THE DIAGONAL OR FROM THE WORK SIZE (%)	ISO 10545-2	±0.75mm [7≤N<15] ±0.5% (≤±2mm) [N≥15]	COMPLIES
SURFACE QUALITY	ISO 10545-2	95%	COMPLIES
WATER ABSORPTION	ISO 10545-3	<0.5%	COMPLIES
BENDING STRENGTH - BREAKING STRENGTH (N) - RUPTURE MODULE (N/mm ²)	ISO 10545-4	≥ 1300 (Thickness ≥ 7.5 mm) ≥ 700(Thickness < 7.5 mm) ≥ 35	COMPLIES COMPLIES
RESISTANCE TO DEEP ABRASION (mm³)	ISO 10545-6	NOT APPLICABLE	~
RESISTANCE SURFACE ABRASION (PEI)	ISO 10545-7	ACORDING TO TEST REPORT	4
STAINING RESISTANCE	ISO 10545-14	Min. Class 3	5
CHEMICAL RESISTANCE - ACID RESISTANCE - ALKALI RESISTANCE - RESISTANCE TO HOUSEHOLD CHEMICALS AND SWIMMING POOL SALTS	ISO 10545-13	as per manufacturer as per manufacturer MIN. B	LA LA A
LINEAR THERMAL EXPANSION - COEFFICIENT OF LINEAR THERMAL EXPANSION (K-1)	ISO 10545-8	as per manufacturer	< 9.0x10 ⁻⁶
CRAZING RESISTANCE	ISO 10545-11	REQUIRED	COMPLIES
FROST RESISTANCE	ISO 10545-12	REQUIRED	COMPLIES
THERMAL SHOCK RESISTANCE	ISO 10545-9	RESISTANT	COMPLIES
MOISTURE EXPANSION	ISO 10545-10	< 0.6mm/m	COMPLIES
ANTI-SLIP PROPERTIES - WORKROOMS AND FIELDS OF ACTIVITIES WITH RAISED SLIP DANGER - WET-LOADED BAREFOOT AREAS	DIN 51130 DIN 51097	as per manufacturer, when applicable as per manufacturer, when applicable	R10 A
ANTI-SLIP PROPERTIES	ENV 12633	as per manufacturer, when applicable	Class 2
ANTI-SLIP PROPERTIES - WET AREAS - DRY AREAS	BS 7976	as per manufacturer, when applicable as per manufacturer, when applicable	≥ 36 ≥ 36
IMPACT RESISTANCE COEFFICIENT OF RESTITUTION	ISO 10545-5	≥ 0.55	~

GPN3060FRE201_V0


 GRESKO - Grés de Coimbra, S.A.
 APARTADO 19 3771-909 OLIVEIRA do BAIRRO
 PORTUGAL

Tel.: (351) 239 980050 Fax.: (351) 239 983919 gresco@gresco.pt

Technical Direction

Administration

Date

20, 06, 2021